Bh AZ

group nor a methacrylic group, said polymer being present in said polymer resin layer in an amount of 80% by weight or more based on said polymer resin layer.

## **REMARKS**

The claims of this application have been amended to put them in a format generally adopted in the United States. This amendment does not introduce any new limitation and, therefore, does *not* narrow the claims.

Attached hereto is a marked-up version of the changes made to the specification and claims by the current amendment. The attached page is captioned "Version with markings to show changes made"

In the event that the transmittal letter is separated from this document and the Patent and Trademark Office determines that an extension and/or other relief is required, applicant petitions for any required relief including extensions of time and authorizes the Commissioner to charge the cost of such petitions and/or other fees due in connection with the filing of this document to **Deposit Account No. 03-1952**, reference No. <u>360842007400</u>. However, the Commissioner is not authorized to charge the cost of the issue fee to the Deposit Account.

Dated: March 13, 2001

Respectfully submitted,

Raj 8. Davé, Ph.D., J.D.

Registration No. 42,465

Morrison & Foerster LLP 2000 Pennsylvania Avenue, N.W.

Washington, D.C. 20006-1888 Telephone: (202) 887-8798

Facsimile: (202) 263-8396

## **VERSION WITH MARKINGS TO SHOW CHANGES MADE**

## In the Claims:

Claims 1-20 have been amended as follows:

1. (Amended) A multilayer film comprising a base material, a polymer resin layer and a metal deposited layer and/or a metal oxide deposited layer provided on the base material, wherein said polymer resin layer [contains] comprises a polymer produced by polymerization of an unsaturated compound having two or more ethylenic bonds and/or acetylenic bonds in one molecule and having neither an acrylic group nor a methacrylic group, said polymer being present in said polymer resin layer in an amount of 80 % by weight or more based on said polymer resin layer.

- 2. (Amended) A multilayer film according to claim 1, [in which] wherein the polymer resin layer, the metal deposited layer and/or the metal oxide deposited layer are provided on the base material in this order.
- 3. (Amended) A multilayer film according to claim 1, [in which] wherein the metal deposited layer and/or the metal oxide deposited layer and the polymer resin layer are provided on the base material in this order.
- 4. (Amended) A multilayer film according to claim 1, [in which] wherein the thickness of the polymer resin layer is not less than 0.02 μm and not more than 1 μm.
- 5. (Amended) A multilayer film according to claim 4, [in which] wherein the thickness of the polymer resin layer is not less than 0.05 μm and not more than 0.5 μm.

7

- 6. (Amended) A multilayer film according to claim 1, [in which] wherein the unsaturated compound is one or more compounds selected from the group consisting of an unsaturated fatty acid, an unsaturated fatty ester, and a terpene having an unsaturated bond.
- 7. (Amended) A multilayer film according to claim 6, [in which] wherein the unsaturated fatty acid, unsaturated fatty ester, and terpene having an unsaturated bond are compounds isolated from natural substances.
- 8. (Amended) A multilayer film according to claim 7, [in which] wherein the unsaturated fatty acid, unsaturated fatty ester, and terpene having an unsaturated bond are compounds selected from the group consisting of a drying oil, a semi-drying oil, or a hydrolysate thereof, or a part of the component thereof, or a combination thereof.
- 9. (Amended) A multilayer film according to claim 8, [in which] wherein the drying oil or the semi-drying oil is a compound having an iodine value of not less than 100.
- 10. (Amended) A multilayer film according to claim 6, [in which] wherein the unsaturated fatty acid, unsaturated fatty ester, and terpene having an unsaturated bond are one or more compounds selected from the group consisting of castor oil, coconut oil, soybean oil, linseed oil, palm kernel oil, safflower oil, china wood oil, tall oil, oleic acid, linolic acid, linolenic acid, ricinoleic acid, eleostearic acid, triglyceride linoleate, triglyceride linolenate, citral, citronellal, citronellol, nerolidol, geraniol, milsen, linalool, and limonene.

- 11. (Amended) A multilayer film according to claim 1, [which is used for] said multilayer film having a property of a metallized packaging film or a metallized film for a capacitor.
- 12. (Amended) A process for producing a multilayer film, comprising [in which] forming a polymer resin layer on a base material and depositing a metal [deposited] layer and/or a metal oxide [deposited] layer [are deposited] on [a] the base material [in a vacuum deposition apparatus], wherein said forming a polymer resin layer comprises depositing an unsaturated compound having two or more ethylenic bonds and/or acetylenic bonds in one molecule and having neither acrylic group nor methacrylic group on the base material, [is deposited,] and then irradiating the unsaturated compound [is irradiated] with energy rays [to form said polymer resin layer].
- 13. (Amended) A process for producing a multilayer film according to claim 12, [in which] wherein the metal and/or the metal oxide is deposited on the base material[,] and then said unsaturated compound is deposited on said metal [deposited] layer and/or metal oxide [deposited] layer [and said unsaturated compound is irradiated with energy rays to form the polymer resin layer].
- 14. (Amended) A process for producing a multilayer film according to claim 12, [in which] wherein said unsaturated compound is deposited on the base material[,] and [said unsaturated compound is] irradiated with energy rays to form the polymer resin layer, and then the metal and/or metal oxide is deposited on said polymer resin layer.

- 15. (Amended) A process for producing a multilayer film according to claim 12, [in which the] wherein a surface of the base material is [previously] subjected to a plasma treatment prior to said forming a polymer resin layer and depositing a metal layer and/or a metal oxide layer.
- 16. (Amended) A process for producing a multilayer film according to claim 12, [in which] wherein the energy rays are [one or more kinds of energy rays] selected from [a] the group consisting of ultraviolet rays, ions, excited atoms, and excited molecules.
- 17. (Amended) A process for producing a multilayer film according to claim 12, [in which] wherein the energy rays are a plasma of a gas containing oxygen atoms.
- 18. (Amended) A process for producing a multilayer film according to claim 12, [in which] wherein the [deposition of] depositing the unsaturated compound on the base material [is such that] comprises atomizing the unsaturated compound [is] to form atomized particles and [allowed] impinging said atomized particles [to impinge upon] on a [heated] wall of [an] a heated apparatus [thereby evaporated and deposited on the base material or the metal and/or metal oxide deposited layer].
- 19. (Amended) A process for producing a multilayer film according to claim 18, [in which] wherein the unsaturated compound is atomized by applying an electric voltage to the unsaturated compound.

20. (Amended) A process for producing a multilayer film according to claim 18, [in which] wherein [the unsaturated compound is atomized and allowed to impinge upon a wall of a heated apparatus thereby evaporated and deposited on the base material or the metal and/or metal oxide deposited layer through an aperture of] a wall of said heated apparatus comprises an aperture, wherein the unsaturated compound is deposited while an electric voltage is applied between the aperture [of said heated apparatus] and the metal [deposited] layer and/or metal oxide [deposited] layer.

Claims 21 and 22 have been added:

21. A process for producing a multilayer film according to claim 12, wherein said forming a polymer resin layer and depositing a metal layer and/or a metal oxide layer on a base material is in vacuum.

22. A multilayer film comprising a base material, a polymer resin layer and a metal layer and/or a metal oxide layer provided on the base material, wherein said polymer resin layer comprises a polymer produced by polymerization of an unsaturated compound having two or more ethylenic bonds and/or acetylenic bonds in one molecule and having neither an acrylic group nor a methacrylic group, said polymer being present in said polymer resin layer in an amount of 80% by weight or more based on said polymer resin layer.